CORROSION CONTROL LINING SYSTEMS



HYDRO-POX 212GL

DESCRIPTION:

HYDRO-POX 212 GL is a time proven 100% solids, 2-component, silica extended, fiber reinforced 2:1 by volume Epoxy Grouting/Lining System. HYDRO-POX 212 GL offers single coat film build to 80-150 mils vertical and overhead. Its unique formulation allows application by roller or spray, eliminating the labor-intensive process of trowel application to achieve high film builds. HYDRO-POX 212 GL combines the unique features of broad chemical resistance to acid bases. HYDRO-POX 212 GL cures down to 40F and completely cures at 100% relative humidity. High film build is obtained in a single coat, multiple pass application with NO VOC'S and extremely quick turn around time. Several Wastewater Agency approvals.

USES:

Designed as a monolithic corrosion control lining system for immersion and non-immersion applications to protect steel, cast iron, concrete, FRP and other substrates in above and below grade water, wastewater and chemical containment, and atmospheric applications.

Typical Applications include but are not limited to:

- All Potable Water Tanks, Pipes, Treatment Structures; Concrete and Steel.
- All Wastewater Tanks, Pipes, Treatment Structures; Concrete and Steel.
- Secondary Containment of all Process Chemicals used in the treatment of Potable Water and Wastewater, other chemical process industries.
- Repair of existing Coal tar, Coal tar epoxy, FBE, and Epoxy linings.
- All minimum downtime applications above and below grade.

APPLICATION INSTRUCTIONS:

LIMITATIONS:

Apply when substrate temperatures are above 40F. For optimum application properties, bring material to 70-80F prior to mixing and application. Unmixed material should be maintained in protected storage between 40-100F. Always mix a complete unit.

SURFACE PREPARATION:

CLEAN ALL SURFACES. Substrate must be sound, clean, free from oil and grease. Curing compound residues and any foreign matter must be thoroughly removed. Surface preparation is best accomplished by mechanical means, such as abrasive air blasting or by high pressure water blasting. For immersion service on steel an SSPC SP-10 is a recommended minimum. For immersion or gas area service on concrete reference applicable SSPC/NACE/ASTM Standards.

APPLICATION:

- Mix ratio: 2:1 by volume (Always mix a complete unit.)
- Gel time @ R.T. (200 gram mass): 50 minutes, (3-gallon mass): 25 minutes
- Method of Application: Brush, Roll, Trowel, Squeegee or Spray(Parastalic pump)
- Application Temperature Range 40-140F
- Thinner: NOT RECOMMENDED

 Clean up: MEK, Lacquer Thinner, Toluene, and Xylene. Cured materialmechanical removal.

Temp.	Pot Life	Cure Time	Minimum Recoat	Maximum Recoat
(F.)	(Hrs: Min)	(Hours)	Time (Hours)	Time (Hours)
50	0:50	48	no minimum	24
77	0:25	24	no minimum	12
90	0:15	12	no minimum	same day

Note: The above values are approximate depending on coating thickness and surface temperatures. Below 40F cure is significantly retarded and film properties may be degraded.

MIXING:

Material is supplied as a unit. Pre-condition material to between 70-80F. Always mix a complete unit in the proportions supplied. For 3-gallon kits, combine entire contents of "A" and "B" components and mix thoroughly for 3 minutes or until material is completely homogenous, with a power mixer, apply immediately.

THINNING:

DO NOT THIN. For optimum application properties, bring material to 70-80F prior to mixing and application.

CLEAN-UP

Clean all tools immediately after use with Toluene, Xylene, MEK, or Lacquer thinner. It is good practice to periodically flush spray equipment during the course of the day – certainly before any work stoppage for lunch breaks etc.

PACKAGING/STORAGE:

HYDRO-POX 212GL is available in 3-gallon kits, consisting of 2-gallons "A" Component in a 5-gallon pail, 1-gallon of "B" Component within the same 5-gallon pail. All containers should be kept closed in dry protected storage between 40-100F.

HEALTH AND SAFTY:

Before use all operators and applicators must consult the Material Safety Data Sheet (Parts A and B). Wear Protective clothing, gloves, goggles, and organic vapor respirator.

DISCLAIMER AND LIMITED WARRENTY:

CCI/CON-TECH OF CALIFORNIAM INC. warrants its product to be free of manufacturing defects. Our products will meet our published physical properties when applied in accordance with our directions and tested in accordance with our standards. Proven defective material will be replaced on a limited one-year warranty. Applicators have a legal responsibility for proper application methods as per instructions and specifications. There are no warranties by CCI of any nature whatsoever, expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. CCI shall not be liable for any damages of any sort, including any removal or consequential damages, resulting from any claimed breech of implied, including any warranty of merchantability or fitness for a particular purpose, or from any other cause whatsoever. CCI shall also not be responsible for the use of this product in a manner to infringe on any patent held by others.